



TECHNICAL DATA SHEET

Version 1
01/03/17

FULLABOND 95

Type of Adhesive FULLABOND 95 is a versatile, high solids adhesive that has many applications..

Product Benefits FULLABOND 95 has high initial tack, good grab and a very fast set speed

Typical Applications FULLABOND 95 Can be used for closure of packets on high speed equipment where laminated or wax art board is used .laminating supported and unsupported PVC (polyvinyl chloride) films to porous substrates such as hardboard, plywood, etc. Head bands and casing-in. Bonding of certain films, foil and plain and coated papers.

Typical Properties

Raw material base	Synthetic polymer emulsion
Appearance	White
Viscosity	5,000 – 7,000 cps
Solids (%)	53 - 57
Specific Gravity	Circa 1.06
Application information	FULLABOND 95 is designed to be applied by nozzle, wheel or roller and runs on most types of equipment. Ensure substrates are free form oils dirt or grease. For optimum performance this product should be used within operating temperatures of 15°C to 30°C.
Limitations	Check machine and material compatibility prior to commercial use.
Storage	Product should be stored in the original container out of direct sunlight between 5°C and 30°C and protected from freezing. Rotate stock using oldest batches first. Close containers air tight after use.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 22225588





TECHNICAL DATA SHEET

Shelf life	12 months
Clean-up	After use, brushes, rollers, glue baths and other equipment should be washed with warm water before the adhesive dries out.
FDA(Food and Drug Administration)	21 CFR 175.105 Adhesives
Safety Advice	Please refer to the SDS for safety advice.

Made in Australia

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
 Tel: +61 1800 423 855
 customer.service@hbfuller.com
China & Hong Kong
 Tel: +86 20 82068291
 cs.china@hbfuller.com
Indonesia
 Tel: +62-21-5307232/33

Korea
 Tel: +82 2 786 8296
 cskorea@hbfuller.com
Malaysia
 Tel: +603 3345 5200
New Zealand
 Tel: +64 800 555 072
 customer.service@hbfuller.com

Philippines
 Tel: +63 2 5194073
Taiwan
 Tel: +886 2 26033385
Thailand
 Tel: +66 2 3757442
Vietnam
 Tel: +84 8 2225588

