

## **TECHNICAL DATA SHEET**



Version 2 22/01/19

# **FULLABOND 139 LV**

- **Type of Adhesive** FULLABOND 139 LV is a fast setting adhesive designed for the forming of cartons through medium to high speed equipment where standard corrugated board is used. FULLABOND 139 LV has also proved successful in the bonding and construction of formed paper cores, particularly thinned walled minimum ply toilet tissue cores.
- Product BenefitsFULLABOND 139 LV has a high initial tack level and good grab. It has a<br/>fast set speed and has fair degree of water resistance
- **Typical Applications** Used extensively for flat board lamination and plasterboard side seaming.

Raw material base	Synthetic polymer emulsion
Appearance	Blue OR White creamy liquid
Viscosity (Brookfield # 4/20/25°C)	1,500 – 1,700 cps
Solids (%)	37 - 41
Specific Gravity	Circa 1.06
Application information	FULLABOND 139 LV is primarily designed to be applied by wheel, roller, cascade coater or nozzle. For optimum performance this product should be used within operating temperatures of 15°C to 30°C.Ensure substrates are free form oils dirt or grease. Depending on application equipment used product maybe diluted if required.
Limitations	Check machine and material compatibility prior to commercial use.
Storage	Product should be stored in the original container out of direct sunlight between, 15°C to 25°C and be protected from freezing. Rotate stock using oldest batches first. Close containers air tight after use.
Shelf life	12 months

#### **Typical Properties**

#### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including putpice), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com Indonesia Tel: +62-21-5307232/33 Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com

 Philippines

 Tel: +63 2 5194073

 Taiwan

 Tel: +886 2 26033385

 Thailand

 Tel: +66 2 3757442

 Vietnam

 Tel: +84 8 22225588







## **TECHNICAL DATA SHEET**

Clean-up	Clean up adhesive while wet with warm water.
FDA(Food and Drug Administration)	21 CFR 175.105 Adhesives
Safety Advice	Please refer to the SDS for safety advice.

## Made in Australia

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tot (including negligence), breach of statutory duty, misrepresentation, strict liability of thereine of affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com Indonesia Tel: +62-21-5307232/33 Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com

 Philippines

 Tel: +63 2 5194073

 Taiwan

 Tel: +886 2 26033385

 Thailand

 Tel: +66 2 3757442

 Vietnam

 Tel: +84 8 22225588

