



TECHNICAL DATA SHEET

Version 1 01/03/17

FULLABOND 1200

Type of Adhesive

FULLABOND 1200 is a versatile, high solids product that has many applications.

Typical Applications

FULLABOND 1200 is suitable for paper laminating or winding.

Typical Properties

Raw material base	Synthetic polymer emulsion
Viscosity	1,500 – 2,000 cps
Solids (%)	53 – 56
Application information	For optimum performance this product should be used within operating temperatures of 15°C to 30°C.Ensure substrates are free form oils dirt or grease.
Limitations	Check machine and material compatibility prior to commercial use.
Storage	Product should be stored in the original container out of direct sunlight between 15°C and 30°C and be protected from freezing. Rotate stock using oldest batches first. Close containers air tight after use.
Shelf life	12 months
Clean-up	Clean up adhesive while wet with warm water.
Safety Advice	Please refer to the SDS for safety advice.

Made in Australia

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com

Indonesia

Tel: +62-21-5307232/33

Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com Philippines Tel: +63 2 5194073 Taiwan Tel: +886 2 26033385 Thailand Tel: +66 2 3757442 Vietnam

Tel: +84 8 22225588

