



TECHNICAL DATA SHEET

Version 7 01/02/2017

FULLAMELT 4955

Type of Adhesive FULLAMELT 4955 is a light colored, hot melt adhesive with excellent

> machining characteristics. It has very good heat stability and heat resistance. This product has been formulated specifically for case and carton sealing and general packaging where a fast setting hot melt is

required.

Product Benefits Light colour

> **Excellent heat stability** Excellent heat resistance

Typical Applications Case and carton sealing

Typical Properties

Raw material base	Synthetic resin & polymer
Colour	Pale Straw/Light Amber
Ring & Ball	ca. 116°C
Viscosity (Spindle 21, 20RPM, 177°C)	ca. 900 – 1,100 cP
Application Temperature Range	170 – 190°C
SAFT(Shear Adhesion Failure Temperature)	ca. 93°C
PAFT(Peel Adhesion Failure Temperature)	ca. 69°C
Speed of Set	Fast
Shelf Life	1 Year
Safety Advice	Please refer to the SDS for safety advice.

Made in Australia

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a quarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia Tel: +61 1800 423 855 customer.service@hbfuller.com China & Hong Kong Tel: +86 20 82068291 cs.china@hbfuller.com

Indonesia Tel: +62-21-5307232/33

Korea Tel: +82 2 786 8296 cskorea@hbfuller.com Malaysia Tel: +603 3345 5200 New Zealand Tel: +64 800 555 072 customer.service@hbfuller.com **Philippines** Tel: +63 2 5194073 Taiwan Tel: +886 2 26033385 Thailand Tel: +66 2 3757442 Vietnam

Tel: +84 8 22225588

