



TECHNICAL DATA SHEET

Version 1
01/07/17

FULLATAK C519

DESCRIPTION:

Fullatak C519 is a brush/roller grade, polychloroprene solvent based adhesive. Fullatak C519 was especially formulated for adhering PVC and carpet to vertical surfaces. Fullatak C519 bonds well to the following substrates, plastic laminates, particle board, plywood, hardboard, wood, render, steel, aluminium, brick, rubber, leather and polyurethane foam

CHARACTERISTICS

- Highly flammable
- Aggressive tack
- High bond Strength
- Excellent water resistance
- Excellent heat resistance
- Dry film will not support combustion
- Coverage; 4-6m²/ltr

PREPARATION

All subfloor surfaces shall be dry, smooth, sound and clean, free of wax, grease, oil, old adhesive, paint, curing compounds, laitance, bond breakers and all other contaminants that inhibit adequate adhesion to the sub-floor. The sub-floor must also be free from hydrostatic pressure or capillary action. The adhesive should not be used in excessive cold or hot conditions i.e. below 8°C or above 28°C.

Uneven or damaged floors should be repaired with a cementitious levelling compound. All substrates should be tested for moisture content prior to the application of this adhesive. If the substrate is concrete, the moisture content should not exceed 5.5% and or the relative humidity should not exceed 70%. Do not use this adhesive if the moisture content /relative humidity levels are above the acceptable standards. All subfloors should in accordance with current Australian standard installation practices.

APPLICATION

Thoroughly stir adhesive before use. Brush on an even film of adhesive to both surfaces, for best results coat one surface from side to side and on the second surface top to bottom. Wait until touch dry (normally 10-15 mins) but no longer than 30 mins. Ensure surfaces are positioned correctly and then press the two surfaces firmly together. An instant bond will result. Maximum bond strength will develop after approximately 24- 48 hours.

HEAT REACTIVATED CONTACT BONDING: METHOD:

After the adhesive coated surfaces have thoroughly dried (up to several hours) then heat to 82-93°C, then while hot and tacky combine and press. Leave to cool.

HANDLING PRECAUTIONS

This product is flammable. Use only in well ventilated areas. Keep away from heat, sparks and naked flames. Avoid contact with skin and eyes. Avoid breathing vapours, if swallowed do not induce vomiting.

VENTILATION

Always make sure that there is adequate ventilation when using this adhesive.

CONDITIONS OF SALE:

contain a limited warranty against manufacturing defects.

NOTICE TO THE PURCHASER

All statements and technical information contained herein are based on tests we believe to be reliable but the accuracy thereof is not guaranteed. Users assume all risk and liability resulting from the use of this product and must confirm the suitability thereof by their own tests.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia
Tel: +62-21-5307232/33

Korea
Tel: +82 2 786 8296
cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam
Tel: +84 8 22225588